

# Fluorolink® E10-H

## Perfluoropolyether

Fluorolink® E10-H is a dialcohol terminated, ethoxylated PFPE. Thanks to its functional hydroxyl end-groups, can be used to modify polymers such as urethanes, esters, epoxies and acrylates.

Fluorolink® E10-H is especially suitable as a building block and polymer modifier for those applications that require a combination of excellent water and oil repellency, easy removal of graffiti and fingerprints, low friction, low refractive index and high chemical resistance.

Property	Typical Value	Unit	Test Method
Functional groups	Ethoxylated alcohol		
Average molecular weight (NMR)	1,700	amu	
Fluorine content	57	% w/w	
Kinematic viscosity at 20 °C	115	cSt	
Density at 20 °C	1.69	g/cm <sup>3</sup>	
Appearance	Clear, light yellow liquid		

[www.solvay.com](http://www.solvay.com)

[SpecialtyPolymers.EMEA@solvay.com](mailto:SpecialtyPolymers.EMEA@solvay.com) | Europe, Middle East and Africa

[SpecialtyPolymers.Americas@solvay.com](mailto:SpecialtyPolymers.Americas@solvay.com) | Americas

[SpecialtyPolymers.Asia@solvay.com](mailto:SpecialtyPolymers.Asia@solvay.com) | Asia Pacific

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products. Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. All trademarks and registered trademarks are property of the companies that comprise Solvay Group or their respective owners.

© 2015 Solvay Specialty Polymers. All rights reserved. R 07/17/2015 | Version 2.3 Design by ahlersheinel.com